



Ty-Mawr Purpose General Filler is a non-shrink, ready mixed mortar made with natural hydraulic lime, siliceous and calcareous sand (0-0.6mm) and additives. Suitable for repairing or restoring cement renders, lime plasters and refurbishment work on composite backgrounds.

## Instructions for Use

- The surfaces should be clean and grease-free. Any loose material should be brushed off.
- Moisten highly absorbent surfaces with water prior to application.
- 1 kg of Filler should be **vigorously** mixed with 200-250 ml water until a lump free paste is obtained.
- Apply filler to create an even surface. Do not apply in layers greater than 20mm. If necessary level-out deep holes and cracks a second time.
- Fine cracks will need to be opened up to a width of at least 5mm before filling.
- Use the filler within 4 hours, do not rework.
- If you are unsure about the appropriateness of this product for your specific application then please contact Ty-Mawr.

Water addition: 200 to 250ml per 1 kg.

**Consumption**: 1.7kg per mm of thickness per m<sup>2</sup>.

**Shelf life:** 12 months if kept in dry storage conditions.

Granulometries: 0-0.6mm.

## Health and Safety Information WARNING



Skin Irritation 2 H315 Causes skin irritation. STOT SE 3 H335 May cause respiratory problems.

DANGER



Eye Damage 1 H318 Causes serious eye damage.

## Precautionary Statements

P102 Keep out of reach of children. P280 Wear protective gloves, eye protection/face mask.

P305 + P351 + P310 If in eyes rinse cautiously with water for several minutes and immediately get medical assistance. P352 + P352 If on skin, wash affected parts immediately with plenty of soap and water.

© Copyright - please do not infringe our copyright by copying or reproducing any part of this document.

Disclaimer - no responsibility can be accepted for any errors or omissions or any loss or damage as a result of using the information provided in these guidines.

Distribution warehouse: Unit 12, Brecon Enterprise Park, Brecon, Powys LD3 8BT Tel: 01874 611350 Fax: 01874 658502 Email: tymawr@lime.org.uk www.lime.org.uk

