



Manufacturer and supplier of traditional and environmentally-friendly building materials.

COULINEX®

LIME GROUTING AND INJECTION



THE + BENEFITS

- **BASED ON SAINT-ASTIER LIME®**
- **NO CEMENT OR POZZOLANIC ADDITION**
- **STABLE GROUT**
- **VERY LITTLE SETTLING**
- **INJECTABLE INTO ALL TYPES OF CAVITIES**
- **COMPATIBLE WITH PLASTER & MASONRY**

AREAS OF USE

- > **COULINEX® L** can be used on its own for fine cracks or mixed with sand of any particle size for larger cavities.
- > **COULINEX® M** is used for cavities or cracks up to 5 mm.

PACKAGING

- > **COULINEX® L**: 25 kg bag
40 bags per pallet (1T)
- > **COULINEX® M**: 20 kg bag
56 bags per pallet (1T120)

COMPOSITION

- > **COULINEX® L**: natural hydraulic lime, fillers and specific additives.
- > **COULINEX® M**: natural hydraulic lime, fillers, sand less than 1 mm and specific additives.

SHELF LIFE & GUARANTEE

One year from production date if protected in the original packaging and stored in dry conditions.
Manufacturer civil responsibility.

RESTORATION RANGE

CONSOLIDATION BINDER AND MORTAR



Manufacturer and supplier of traditional and environmentally-friendly building materials.

EXPECTED PERFORMANCES FOR COULINEX L

DOSAGE	100% COULINEX + WATER	50% COULINEX / 50% SAND 400µ-200µ + WATER	75% COULINEX / 25% SAND 400µ-200µ + WATER	
SO ₄ content %	0	0	0	Should not be above 0.5%
Organic content %	0	0.2	0.2	Should not be above 1%
Bulk density (g/l)	579	996.5	894	Powder only
Water addition (g)	875	375	600	Per kg. of powder
Fluidity Marsh cone 10mm	24	13	16	Should be between 13 and 25 seconds
Stability * % at 3h	1.05	0.25	0.2	Should be < 3% at 3 hours
Stability * % at 24h	1	0	0	Should be NIL at 24 hours
Comp. Strength (N/mm ²)	1.35	1.43	3.17	28 days cured 7 days in the mould and dried before testing
Tens. Strength (N/mm ²)	0.31	0.55	1.07	
Bulk density (g/l)	1383	1768	1605	
Comp. Strength (N/mm ²)	4.87	4.48	5.18	90 days
Tens. Strength (N/mm ²)	1.32	2.27	2.91	
Bulk density (g/l)	1381	1828	1632	
Comp. Strength (N/mm ²)	5.18	5.20	6.0	180 days
Tens. Strength (N/mm ²)	1.41	1.42	1.63	
Bulk density (g/litre)	1378			



Manufacturer and supplier of traditional and environmentally-friendly building materials.



SUITABLE SUPPORTS





- > Old brick, stone and timber frame supports.







SUBSTRATE PREPARATION

- > Moisten the cavities the day before grouting.
- > Make sure that the masonry joints are tightly sealed so that the grouting goes not spill over.
- > For the injection, holes 20 to 30 mm in diameter and inclined at 45° should be drilled to a depth of around 90% of the thickness of the wall. These holes should be spaced at intervals equal to the thickness of the wall.
- > The operation will be repeated at heights varying from 1 to 2 times the thickness of the wall.
- > Mix mechanically (preferably with a whisk) for 2 to 4 minutes.
- > The mixture can be mixed in a cement mixer for a maximum of 5 minutes.
- > The amount of water can be adjusted according to the porosity of the substrate.

GROUT PREPARATION - APPLICATION

COULINEX® L (binder) 25 kg bag	
Binder for fine grouting	
 + 	= 30 litres of grout

COULINEX® M (mortar) 20 kg bag	
Grouting mortar	
 + 	= 14,5 litres of grout
 + 	= 7,2 litres of grout

COULINEX® L (binder) 25 kg bag + sand	
Binder for casting cavities	
 +  + 	= 50 litres of grout
 +  + 	= 13 litres of grout

- > Mix mechanically until a homogeneous consistency is obtained.
- > Workability: approximately 3 hours depending on weather conditions.
- > The water content may vary depending on the substrate, but the mixing time remains constant.

The aggregates that can be combined range from 0/0.5 mm for the finest to 0/4 mm for the coarsest. The maximum diameter of the sand must be 4 times smaller than the size of the voids to be grouted.

- > **Technical Implementation Documents (DTMO)** are available at : www.stastier.co.uk.

TECHNICAL CHARACTERISTICS

COULINEX® L (Binder) 25 kg bag

- > Powder bulk density According to NF EN 459-2 : 0.580 kg / litre
- > Particle size (NF 1015-1)
Retained 80 µm : 3 to 7%.
Retained at 200 µm : 0 to 1%.
Retained at 500 µm : 0%.
- > Apparent density paste According to NF EN 1015-6 : 1.5 Kg / l
- > Setting time (EN 196-3) : 21 hours
- > Compressive strength
28 days - NF EN 1015.11, EN 196-1 : 1.35 MPa
90 days - NF EN 1015.11 : 4.9 MPa
- > Flexural strength
28 days - NF EN 1015.11 : 0.3 MPa
90 days - NF EN 1015.11 : 1.4 MPa

COULINEX® M (Mortar) 20 kg bag

- > Powder bulk density According to NF EN 459-2 : 1 kg / litre
- > Particle size (NF 1015-1) Retained 80 µm : 65 to 75%.
Retained at 200 µm : 60 to 70%.
Retained at 500 µm : 5 to 10%.
Retained at 500 µm : 0%.
- > Apparent density paste According to NF N 1015-6 : 1.9 Kg / l
- > Setting time (EN 196-3) : 15 hours
- > Compressive strength
28 days - NF EN 1015.11, EN 196-1 : 1.5 MPa
90 days - NF EN 1015.11 : 3.5 MPa
- > Flexural strength
28 days - NF EN 1015.11 : 0.6 MPa
90 days - NF EN 1015.11 : 1.2 MPa

WEATHER CONDITIONS

Use between 8°C and 30°C.

