

HOUREX a multi use binder

St Astier Natural Hydraulic Limes (NHL)

For building mortars, renders stipple and base coats, roofing, chimneys, floor tiling.

Based on St. Astier natural hydraulic lime with addition of OPC and additives for highly workable and breathable mortars.

	POWDER	Test std.	MORTAR (sand 0-3mm, Volume 1:3)	Test std.
Dry Density	800 g.l. +/-10%	BS459	1425g.l +/- 25g dry 1650g.l +/- 50g wet	EN1015-11 EN 1015-6
Whiteness	40.55	NFX08.012		
Workability (depending on water addition)			210mm +/- 10mm	EN1015-3
Water retention			81% +/- 3%	CSTB 2669-4
Compressive strength 24 hrs 7 days 28 days			1.5 N.mm ² 4-5 N.mm ² 6-7 N.mm ²	BS998.2 BS998.2 BS998.2
Thermal conductivity			0.540 W/m.K	EN 1745
Vapour permeability			1,60.10 ⁻⁹ kg/m ² sPa (0.77g x m ² x h x mmHg)	EN 1015-19
Elasticity moduli			7000 - 9000 MPa	CSTB
Capillarity			0.75 g.min.	
Fire resistance			Class A1 (with silica or calcareous sands)	

Mortar preparation: Up to 5 minutes in conventional drum mixers.

Sand: Clean, well graded 0-3mm (general). Lower or higher granulometries can be adopted.

Avoid monogranular sands. Sands for renders base coats should not be below 0-2mm.

Adequately dampen materials or background if too dry or with high suction. Do not work in temperatures below 5°C or above 35°C. The building materials or background should not be frosty or too hot or water saturated. Protect fresh mortars from frost, rain or strong direct sun. Storage: in dry store. Reseal open bags a.s.a.p

DOSAGES	HOUREX	SAND (0-3mm)	By Volume
Bricks, blocks,	1 bag (25kg)	85 litres	1 : 3 sand
Floor tiling	1 bag (25kg)	85 litres	1 : 3 sand
Roofing	1 bag (25kg)	70 litres	1 : 2.5 sand
Chimneys	1 bag (25kg)	65 litres	1 : 2.25 sand
Renders (base coat)			
Manual application	1 bag (25kg)	70 litres	1 : 2.5 sand
Sprayed application	1 bag (25kg)	60 litres (+/-10%)	1 : 2 sand

The above details are given for general information purposes and do not constitute a specification. For further Guidance, contact your St Astier Distributor.

Copyright © 2016 CESA, Chaux et Enduits de St Astier